

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: H01B 1/22, C08K 7/28, 9/00, 9/02, 9/10, C08L 91/06	A1	(11) International Publication Number: WO 97/15933 (43) International Publication Date: 1 May 1997 (01.05.97)
(21) International Application Number: PCT/US96/15867 (22) International Filing Date: 3 October 1996 (03.10.96) (30) Priority Data: 08/547,043 23 October 1995 (23.10.95) US (71) Applicant: HOECHST CELANESE CORPORATION [US/US]; Route 202-206, Somerville, NJ 08876-1258 (US). (72) Inventors: LONG, Barbara, J.; 408 Bowen Street, Linden, NJ 07036 (US). HAIDER, M., Ishaq; 44 Maple Village Court, Bernardsville, NJ 07924 (US). MENCZEL, Joseph, D.; 43 Johnson Road, Somerset, NJ 08873 (US). STAMATOFF, James, B.; 606 Dorian Road, Westfield, NJ 07091 (US). (74) Agents: GENOVA, John, M.; Hoechst Celanese Corporation, 86 Morris Avenue, Summit, NJ 07901 (US) et al.		(81) Designated States: European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: IMPROVED ELECTRICALLY AND THERMALLY CONDUCTING COMPOSITIONS FOR ACTUATORS		
(57) Abstract This invention discloses a thermally expandable composition for use in actuators. The composition contains about 10-50 volume percent hollow glass spheres in a wax or a polymer. The spheres contain a conducting coating affixed thereon. During use in an actuator, the composition is heated to melt the wax or polymer, when the density of the spheres substantially match the density of the melt, thereby substantially eliminating phase separation. The high thermal conductivity of the composition increases the speed of heat transfer out of the composition during the cooling cycles.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic			SE	Sweden
CG	Congo	KR	Republic of Korea	SG	Singapore
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LR	Liberia	SZ	Swaziland
CS	Czechoslovakia	LT	Lithuania	TD	Chad
CZ	Czech Republic	LU	Luxembourg	TG	Togo
DE	Germany	LV	Latvia	TJ	Tajikistan
DK	Denmark	MC	Monaco	TT	Trinidad and Tobago
EE	Estonia	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	UG	Uganda
FI	Finland	ML	Mali	US	United States of America
FR	France	MN	Mongolia	UZ	Uzbekistan
GA	Gabon	MR	Mauritania	VN	Viet Nam

IMPROVED ELECTRICALLY AND THERMALLY CONDUCTING COMPOSITIONS FOR ACTUATORS

5

Background of the Invention

10

This invention relates to the field of electrically and thermally conducting compositions for actuators. The compositions comprise a thermally expandable material and an additive that is electrically and/or thermally conductive which then causes the thermal expansion.

15

Actuators are generally devices that produce some mechanical motion in repetitive expansion-contraction cycles. While actuators are of many types, certain types of actuators such as ceramic actuators, piezoelectric actuators and the like are described in some detail by K. Uchino, *The Encyclopedia of Advanced Materials*, Vol. 1, pp. 30-35, Pergamon Press, Elsevier Science Inc., Tarrytown, New York (1994). Many actuators use an expandable material as part of their motion-producing action. Expansion is usually achieved by electrical or thermal heating of the expandable material, while contraction is generally achieved by heat transfer out of the expandable material. A commonly used thermally expandable material is a type of wax, although plastics and metals have also been employed in actuators and similar devices that use expandable materials. Waxes have the advantages of a broad range of melting points, and a volume expansion ("ΔV") that occurs at the operating temperatures.

20

The term wax refers to a substance that is a plastic solid at room temperature and melts to form a relatively low viscosity liquid. Waxes are generally a complex combination of organic compounds, especially long-chained organic acids, esters and hydrocarbons.

25

30

35

Waxes include beeswax, waxes taken from plants (e.g., carnauba wax, bayberry wax, and the like), and mineral waxes derived from petroleum or coal. Montan wax is an example of the latter, being derived by solvent extraction of lignite. Paraffin is a well-known type of petroleum wax, obtained by crude oil distillation/separation.

Low molecular weight (about 10,000 g/mole or less) hydrocarbon polymers also form waxes, especially polyethylene and polypropylene waxes; these waxes may be made by polymerization or obtained by thermally degrading higher molecular weight polymers. Unlike other waxes, these polymers tend to contain molecules that are of the same type, although as in all waxes the molecular weights of the molecules vary.

The exact composition of any type of wax varies based on the origin of the wax and the treatment it has undergone. Waxes of the same type may vary in purity, color, melting point, hardness, and other properties and characteristics.

In an actuator containing an expandable material, e.g., wax, the wax expands during the melting process, and the volume expansion drives a piston, and finally the movement of the piston is transferred into some kind of mechanical motion ("actuation"). Operating temperature and degree of expansion are significant factors in actuator performance, but in many applications the speed of expansion and contraction is also important. In a thermally expandable material, for example, the speed depends on how rapidly heat can be transferred into and out of the thermally expandable material, which depends in large part on the thermal

conductivity of the material, as well as the technique used to heat the material.

Common methods of heating the material to expand is electrical or thermal. The disadvantage of many materials, including common waxes, is that they are electrical and thermal insulators, i.e., the electrical and thermal conductivity is low. In an electrically heated actuator, the low value of electrical conductivity of the wax sets a limit to the heating power, thus limiting the heating, which in turn limits the actuation rate. At the same time, the low thermal conductivity limits the cooling, thus limiting the deactivation rate.

Schneider (U.S. Patent No. 5,177,969) recognized the need for rapid heat transfer, and addressed this problem by designing the actuator so that the material was contained in thin passages, increasing the surface area exposed to heating or cooling. However, this may not be a practical design in all actuators, and does not improve the thermal conductivity of the material itself.

A study of thermally expandable polymers is reported by Z. Jang and Z. J. Zhang in "Thermally- and Phase Transformation-Induced Volume Changes of Polymers for Actuator Applications", Journal of Intelligent Material Systems and Structures, Vol. 5, Nov. 1994, pp. 758-763.

Several workers have used metal powders or carbon black to increase thermal conductivity in thermally expandable materials. U.S. Patent Nos. 3,186,230, 3,187,577, 3,234,793, and 3,403,560 teach combining metal powders with thermally expandable materials for use in thermo-actuators. U.S. Patent No. 3,688,582

teaches adding carbon black to the thermally expandable material in a thermometer to improve visibility and/or heat conductivity. Copending patent application, Serial No. _____, filed of even date herewith,
5 discloses wax compositions containing graphite particles that have significantly improved thermal conductivity.

Another technique may be to add a metal powder to the wax. Addition of highly conductive metal powder may
10 benefit raising both thermal and electrical conductivity. However, the disadvantage of adding metal powder to the wax is that it separates from the wax due to the much higher density of the metal powder when the wax melts, especially during the repetitive heating-
15 cooling cycles.

Thus, it is an object of the present invention to provide a highly thermally expandable composition for actuators.

It is another object of this invention to provide
20 a highly thermally conductive expandable composition for actuators.

It is another object of this invention to provide a highly electrically conductive expandable composition for actuators.

25 It is a further object of the present invention to provide an actuator having a rapid response time.

It is yet another object of the present invention to provide an expandable composition which comprises a uniformly blended mixture of an expanding ingredient
30 and a conducting ingredient whose densities are substantially matched when the composition is heated to melt the expanding ingredient so that the ingredients do not separate when heated.

It is still another object of the present invention to provide an actuator which comprises a uniformly blended mixture of an expanding ingredient and a conducting ingredient whose densities are substantially matched during the functioning of the actuator.

It is a further object of the present invention to provide actuators comprising waxes with additives with increased electrical and thermal conductivities without phase separation when the wax melts during the functioning of the actuator.

Other objects and advantages of the present invention will be apparent to those skilled in the art from the following description and the appended claims.

Summary of The Invention

One or more objects of the present invention are achieved by the provision of an expandable composition for use in actuators, comprising a wax or polymer, and a sufficient amount of suitable objects, defined below, which objects are affixed to a suitable electrical or thermal conducting material, such that the expandable composition possesses high thermal and electrical conductivity. During the heating-cooling cycles of the actuator there is substantial matching of the density of the objects and the density of the molten or semi-molten wax or polymer without phase separation. "Suitable objects" are forms of materials such as, for example, hollow spheres, solid spheres, fibers, fibrils, powder and the like, made of glass, metal, plastic, ceramic and the like. The term "affixed" refers to intimate contact, continuous attachment (such as, for example, a uniform coating), or discontinuous

attachment (such as, for example, glued-on pieces of the conducting material on said object). A discontinuous attachment provides thermal conductivity, while a continuous coating provides both electrical and/or thermal conductivity. The conducting material coating on the spheres is preferably a metal coating, such as, for example, silver, aluminum and the like. Spheres are the most preferred form of the "suitable objects", although the other forms referred to above are also to be considered in a similar fashion.

The expandable composition generally contains about 10-50 volume percent of the spheres dispersed in the wax or polymer. The spheres generally have a diameter range of between about 10 μm to about 0.5 mm, and a density range of about 0.6 to 0.9 g/cm^3 . The spheres containing the conductive affixture provide means for electrical and/or thermal heating of the inventive composition. The wax or polymer then melts under the heating, causing the expansion. At the same time, the substantial matching of density of the spheres and of the molten wax prevents phase separation or agglomeration. During cooling, the spheres, due to their high thermal conductivity, cause rapid heat transfer out of the composition, resulting in contraction upon crystallization. In a typical experiment, a 50:50 (volume ratio) of silver-coated hollow glass spheres with an average density of 0.847 g/cm^3 and Montan wax E (from Hoechst AG, Frankfurt, Germany) was used as the expandable composition; increased electrical conductivity as well as thermal conductivity was demonstrated for the composition, which also showed no phase separation over at least ten cycles; there was substantial matching of density

between the hollow spheres and the molten wax of density about 0.85 g/cm^3 , during the expansion process.

Detailed Description Of The Preferred Embodiments

5 The present invention discloses compositions comprising wax or polymer and suitable objects which have been affixed with a conducting material. The terms "suitable objects", "affixed" and "conducting material" are defined above. The description below uses hollow
10 spheres as the suitable objects. The spheres have diameters generally in the range of about $10 \text{ }\mu\text{m}$ to about 0.5 mm and are present in the wax or polymer in amounts of about 10-50 volume percent. The conducting material is preferably a uniform coating on the
15 spheres, with a coating thickness generally in the range of about $0.4\text{-}0.7 \text{ }\mu\text{m}$ on the spheres. The spheres themselves are made of ceramic, metal, plastic or glass, preferably glass, while the conductive coating may be any coating, for example metal, carbon etc.,
20 that is conductive, is uniformly coated on the spheres, and results in suitable density for the coated sphere. Metal coatings are preferred such as, for example, silver, copper, aluminum, gold and the like, as well as mixtures thereof. Many such coated spheres are
25 commercially available, for example, the Metalite Silver SF-20[®] brand silver-coated hollow glass spheres available from PQ Corporation, Valley Forge, Pennsylvania. The following description illustrates the invention wherein the spheres are hollow glass spheres
30 containing a silver coating of thickness in the range $0.4\text{-}0.7 \text{ }\mu\text{m}$ and wax is the expandable constituent. Other additives such as, for example, stabilizers, nucleating agents, softeners, viscosity modifiers and the like may

also be used in the expandable composition. Typical stabilizers of use may be anti-oxidants many of which are commercially available under the trade names Irganox 1010[®], Irganox 1425[®], Weston 618[®] and Ultrinox U626[®].

In one preferred embodiment of the present invention, 50% by volume silver-coated hollow glass spheres described above, are blended with a suitable wax in a suitable container to substantially uniformly disperse the spheres in the wax. (Because of matched densities, the volume ratio and the weight ratio are substantially the same and the two terms are interchangeable in this disclosure.) The mixture is then heated to temperatures of between about 50-150°C, depending on the thermal stability of the ingredients, and then allowed to cool to ambient temperatures. ("Ambient temperatures" refers to temperatures in the range 20-28°C.) Its thermal and electrical conductivity values are then determined by techniques well known to those skilled in the art. In a typical experiment, 50 grams of the Metalite Silver SF-20[®] brand spheres were taken together with 50 grams of the Montan Wax E (density of melted wax 0.85 g/cm³) in a glass beaker and mixed well. The mixture was then heated on a hot plate to about 110°C with stirring whereupon the wax melted. The solution was then allowed to cool to ambient temperatures, whereupon a uniformly dispersed solid mixture was obtained. The resulting composition was found to have a high electrical conductivity (low resistance of about 1 ohm-cm) in the state of melt (about 120°C), which is substantially higher than that of wax alone which is an insulator. The thermal conductivity of the composition, as measured by the

flux method described by M. R. Kamal et al, *Advances in Polymer Technology*, Vol. 3 (No. 2), 89 (1983), was found to be 0.3 watts/(meter °C) at ambient temperatures, which is three times that of wax alone.

5 This composition can be used in actuators that require a thermally expandable material such as a wax or other material. The composition of the present invention produces a much faster response time for the actuator because the wax can be heated or cooled much
10 more rapidly due to its enhanced thermal transfer rate compared to wax without the spheres. The composition further provides a unique method of matching substantially the density of the wax or polymer by the hollow metal spheres when the wax or polymer (the
15 expanding/contracting ingredient) is in the molten or semi-molten state during the actuating process.

 Although spheres are the most preferred form of the objects in the practice of the present invention, other suitable forms may be employed, such as fibers or
20 fibrils, as stated above and as will be known to those skilled in the art. For example, incorporation of nano-size carbon fibrils/whiskers in a wax matrix forms a molecularly dispersed high conductive network ("percolation") which substantially increases the
25 thermal conductivity of the composition. Such composition provides thermal conductivity enhancement with even small amounts of added fibrils, such as, for example, 10 weight percent.

 When the composition contains objects (e.g.
30 spheres) with a uniform coating of the conducting material on them, the composition possesses electrical and/or thermal conductivity. If it is a discontinuous coating, the composition may only possess enhanced

thermal conductivity. Thus, heating of the composition may be performed electrically and/or thermally depending on the nature of the composition. Furthermore, if it is done electrically, it may be performed by electrical induction or by passing an electrical current through the material, as will be obvious to those skilled in the art. The heating may also be done by suitable thermal means, or by microwave means.

Any type of wax or polymer material that is suitable for use as the thermally expandable material in an actuator may be used in the present invention. Many such waxes are commercially available as Montan wax, polyethylene wax, polypropylene wax, fluoropolymer wax, wax emulsifiers and the like. Some typical trademarked names for useful waxes are, for example, Hoechst Wachs S, LP, E, HP, PE, NE, Ceridust and many such others (available from Hoechst AG, Frankfurt, Germany). It is also within the scope of this invention to use a suitable mixture of a wax and polymer or polymers as the expandable material.

The temperature and technique for blending the glass spheres into the wax material may vary depending upon the materials used, but the selection of the blending method is well within the ordinary skill in the art.

It is preferred that the composition contains about 10-50% by volume of the hollow spheres. In compositions containing less than 10% by volume spheres, the electrical and thermal conductivity may not be increased significantly, and such compositions may not achieve percolation leading to much higher conductivity, whereas compositions having more than 50%

will have such a low proportion of the expandable material that the composition may not expand sufficiently to be useful in the actuator. The skilled practitioner can tailor the composition to achieve a
5 desired combination of conductivities and expansion by thoughtfully selecting the proportion.

Matching of the density of the wax or polymer by the conductive coated spheres when the wax or polymer is in its molten or semi-molten state or during the
10 actuating process is an important and unique advantage of the present inventive compositions. If the densities are not substantially matched, then there is the danger of phase separation of the ingredients during the actuating process. The inventive compositions offer an
15 advantage of such density matching.

The following Examples are presented to illustrate the present invention, but should not be construed as limiting the scope of this invention.

EXAMPLE

20 A wax made by Hoechst AG., known as Hoechst Wachs ETM, was used to prepare compositions for the conductivity tests. A 3 neck round bottom flask, equipped with a mechanical stirrer, thermometer and inlet and outlet for gas was heated on a heating mantle
25 to about 110°C. 50 grams of Metalite Silver SF-20^e hollow glass spheres were added to the flask, followed by 50 grams of the wax. A gentle vacuum was pulled while the wax melted. Upon melting, a slow speed stirring was started. Vacuum was turned off after 2
30 minutes and replaced with nitrogen gas while stirring was maintained at 110°C for 5 minutes. Nitrogen was then stopped, and vacuum was applied again for a minute or two, followed by purging with nitrogen for 10

minutes. The mixture was then allowed to cool to ambient temperature. A tan colored smooth-looking solid was obtained which was tested for thermal and electrical conductivity. Upon melting, no sedimentation of the spheres was noticed, demonstrating that the density of the spheres and the wax were substantially matched. The thermal and electrical conductivities were measured by first compression molding the material into a disk using a vacuum press. The molding conditions for making a 2 inch diameter disk with 1 cm thickness were: 1,000 psi, 80° C and 2 minutes. Using the disk weight and dimensions the density of the molded disk was calculated to be 0.845 gram/cc. The thermal conductivity was measured by the flux method referred to earlier and found to be 0.3 watts/(meter °C). In order to measure the electrical conductivity, the disk was cut and the ends of a section approximately 1.2 cm wide by 0.5 cm thick were painted with Fullam[®] 14811 silver conducting paint (made by Earnest F. Fullam Corporation, Latham, N. Y.). The distance between the painted ends were about 2.0 cm. Measurements were taken with a Beckman Digital Multimeter Tech 310[®] (made by Beckman Instruments, 2500 Harbor Boulevard, Fullerton, CA 92634). From these measurements and the dimensions of the specimen, the volume resistivity was calculated to be 1 ohm-cm.

In order to demonstrate the effect of density matching on phase separation, about 100 grams of the 50/50 Wax E/Metalite Silver SF-20[®] hollow glass sphere mixture was evaluated by a designed experiment simulating the heating-cooling cycles of a typical piston-driven polymer actuator. The mixture was heated from 40°C to 120°C and cooled back to 40°C, repeatedly

and continuously, for 10 cycles. At the end of the tenth cycle, the material was evaluated by conductivity measurements and optical microscopy (using a Leitz[®] optical microscope Model Orthoplan, made by Ernst Leitz, GMBH D-6330, Wetzlar, Germany) for any phase separation and sedimentation. The results showed that the materials remained homogeneous and stable with no signs of phase separation, and no significant affecting of conductivity numbers, thereby demonstrating the unique advantageous aspects of the density-matched wax compositions of the present invention.

Many variations of the present invention not illustrated herein will occur to those skilled in the art. The present invention is not limited to the embodiments illustrated and described herein, but encompasses all the subject matter within the scope of the appended claims.

Claims

1. An expandable composition for use in actuators comprising about 10-50 volume percent of suitable objects in a thermally expandable material, said objects containing a conducting material affixed thereon, wherein said composition is heated by suitable means to melt said expandable material, and further wherein said objects and said expandable material are substantially matched in density during said melting.

2. The composition of claim 1, wherein said expandable material comprises a wax.

3. The composition of claim 1, wherein said expandable material comprises a polymer.

4. The composition of Claim 1, wherein said objects are selected from the group consisting of spheres, fibers, fibrils and powder.

5. The composition of Claim 4, wherein said objects are spheres.

6. The composition of Claim 5, wherein said spheres are hollow spheres.

7. The composition of Claim 5, wherein said spheres are solid spheres.

8. The composition of Claim 6, wherein said hollow spheres are made of glass, metal, ceramic or plastic.

15

9. The composition of Claim 8, wherein said hollow spheres are made of glass.

5 10. The composition of Claim 1, wherein said conducting material is electrically and thermally conducting.

10 11. The composition of Claim 1, wherein said conducting material is thermally conducting.

12. The composition of Claim 1, wherein said affixing material is a continuous coating of said conducting material on said objects.

15 13. The composition of Claim 1, wherein said affixing material is a discontinuous attachment of said conducting material on said objects.

20 14. The composition of Claim 12, wherein said coating has a thickness range of 0.4 - 0.7 mm.

15. The composition of Claim 6, wherein said spheres have diameters in the range 10mm - 0.5 mm.

25 16. The composition of Claim 1, wherein said conducting material is selected from the group consisting of gold, silver, aluminum, copper, carbon and mixtures thereof.

30 17. The composition of Claim 16, wherein said conducting material is silver.

16

18. The composition of Claim 16, wherein said conducting material is aluminum.

19. The composition of Claim 16, wherein said conducting material is copper.

20. The composition of Claim 1, wherein said heating is performed by electrical means.

21. The composition of Claim 1, wherein said heating is performed by thermal means.

22. The compositions of Claim 20, wherein said electrical heating is performed by electrical induction.

23. The compositions of Claim 20, wherein said electrical heating is performed by passing electrical current through said composition.

24. The composition of Claim 1, wherein said heating is performed by microwave energy.

25. An actuator comprising said expandable composition of Claim 1.

26. An expandable composition for use in actuators having a thermal conductivity of at least 0.3 watts/(meter°C) at about 20-25°C, which composition comprises about 10-50 volume percent of hollow glass spheres in a wax, wherein said spheres have a diameter of about 10 mm to 0.5 mm and contain a conductive material of thickness about 0.4 to 0.7 mm affixed thereon, wherein said composition is heated by suitable

means to melt said wax, and further wherein said spheres and said wax are substantially matched in density during said melting.

5

27. The expandable composition of Claim 26, wherein said conductive material is selected from the group consisting of gold, silver, aluminum, copper, carbon and mixtures thereof.

INTERNATIONAL SEARCH REPORT

National Application No.
PCT/US 96/15867

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 H01B1/22 C08K7/28 C08K9/00 C08K9/02 C08K9/10
C08L91/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 H01B C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 409 099 A (OTA TAKASHI ; FUJII KINZOKU KAKO KK (JP)) 23 January 1991 see the whole document ---	1-27
X	EP 0 162 979 A (CAROLINA SOLVENTS INC) 4 December 1985 see the whole document ---	1-27
X	PATENT ABSTRACTS OF JAPAN vol. 013, no. 169 (C-587), 21 April 1989 & JP 63 317541 A (MITSUBISHI METAL CORP), 26 December 1988, see abstract ---	1-27
X	WO 84 02423 A (KENNEDY JOHN W; KENNEDY MALGORZATA TERESA MAND) 21 June 1984 see the whole document ---	1-27
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

& document member of the same patent family

Date of the actual completion of the international search

5 February 1997

Date of mailing of the international search report

21.02.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (- 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (- 31-70) 340-3016

Authorized officer

Leroy, A

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 96/15867

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 91 20088 A (BOURNS INC) 26 December 1991 see the whole document ---	1
A	US 5 006 397 A (DURAND DAVID) 9 April 1991 see the whole document ---	1
Y	US 5 183 593 A (DURAND DAVID ET AL) 2 February 1993 see the whole document -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/15867

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0409099	23-01-91	JP-A- 3047878 CA-A- 2021291 DE-D- 69029174 US-A- 5378533	28-02-91 18-01-91 02-01-97 03-01-95
EP-A-0162979	04-12-85	US-A- 4624865 CA-A- 1256628 JP-C- 1713879 JP-B- 3081241 JP-A- 60254514 US-A- 4624798	25-11-86 27-06-89 27-11-92 27-12-91 16-12-85 25-11-86
WO-A-8402423	21-06-84	AU-A- 2336984 EP-A- 0128919	05-07-84 27-12-84
WO-A-9120088	26-12-91	US-A- 5111178 CA-A- 2085220 EP-A- 0536244 JP-T- 5509440	05-05-92 16-12-91 14-04-93 22-12-93
US-A-5006397	09-04-91	US-A- 4863757 US-A- 4960614 CA-A- 1335190 US-A- 5047260 US-A- 5036128 US-A- 5061551 US-A- 5180513 AT-T- 142405 DE-D- 68927098 EP-A- 0402546 JP-A- 3024788 US-A- 5093038	05-09-89 02-10-90 11-04-95 10-09-91 30-07-91 29-10-91 19-01-93 15-09-96 10-10-96 19-12-90 01-02-91 03-03-92
US-A-5183593	02-02-93	US-A- 5180523 AU-A- 7048091 CA-A- 2068657 DE-A- 4036274 EP-A- 0428165 GB-A, B 2239244 JP-A- 3269909	19-01-93 13-06-91 15-05-91 06-06-91 22-05-91 26-06-91 02-12-91

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/15867

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5183593		WO-A- 9107759	30-05-91
		CN-A- 1054092	28-08-91
		CN-A- 1070417	31-03-93
		US-A- 5531020	02-07-96
		US-A- 5326636	05-07-94

THIS PAGE BLANK (USPTO)